



**Eg-Granuphos**  
**Specs sheet**

**DIRECT APPLICATION PHOSPHATE ROCK (DAPR)**

Parameters	Typical
Fraction of total mass of phosphorus in terms of P2O5, %	24 up to 32 %
Solubility in 2 % citric acid as total	35 % Min
Solubility in 2 % citric acid as P2O5	9 % Min
Fraction of total moisture, %, max	4 % Max.
Granulometry: Fraction of total mass of granules measuring: Under 1 mm, %, max 2 mm to 5 mm, %, min	3% 97 %
Static strength of granules, MPa, not less then	3

■ **Egypt office:** \_\_\_\_\_

Cairo office :

9 Moustafa refaat st. Sherato Heliopolis ,  
Cairo , Egypt

Tel. :+2 22697017 / 18

Fax : +2 22697019

**Alex Office :**  
29 Edmone Fermon,  
Smouha,  
Commercial Building  
Alex, Egypt  
Tel. : +2 03 4256415

[info@movingfert.com](mailto:info@movingfert.com)  
[www.movingfert.com](http://www.movingfert.com)